

CP 250

Clear coat MS 2:1



Resistance to scratches: ●●●●○
 Paint fluidity: ●●●●○
 Gloss: ●●●●○

Unit	Packaging	Collective (box)
1 L + 0,5 L		6 pcs + 6 pcs hard.



**100 parts of CP 250 MS,
50 parts of hardener CP 255 MS.**



Three full layers.
 Spray gun*. Nozzle opening with the pneumatic method: **1.2-1.4 mm**.
 Operating pressure – High-pressure: **3-4 bar***; HVLP: **2 bar***.
 * Use high pressure equipment and HVLP. Pressure as recommended by the gun manufacturer.



Evaporation between the layers (20°C, 65% H.R.): **5 min**.



Drying time 20°C, 65% H.R:
 Dust free: **15 min**
 Air dry: **40 min**
 Prior to assembly: **5 h**
 Through dry: **10 h***

Drying time 60°C, 65% H.R:
 Prior to assembly: **30 min**

* Tests with CP 255 hardener.



Drying IR: **~20 min**

Surface preparation:

Clean surfaces with silicon remover.
 Matt the old coatings in the area of shading.

Pot life:

~6 h

Output:

~7 m²/1L

Thickness of dry coating:

~40-50 µm

Recommended sizes of paint strainers:

125-190 µm

Spray viscosity in 20°C:

18-22 s DIN Cup 4 mm

VOC:

2004/42/WE/IIIB(e)(840)<840

Date of minimum durability:

CP 250: 24 months (in the original unopened package)
 CP 255: 9 months (in the original unopened package)

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products - according to the technical data sheet and execute the sample spray prior to target painting.