

## CP 490

Elastic additive



Elasticizing supplement used to coat car parts made of polymer. Suitable when the use of special supplements for 2K primers and coats is necessary.

Adding **CP 490** to coats and two-component primers enhances the surface elasticity and prevents cracks.

Packaging	
Unit	Collective (box)
250 ml	6 pcs



**100 parts of primer or acrylic paint** mixed with hardener,  
**20-50 parts of CP 490.**



While drying polymer elements, special attention must be paid to high temperature resistance. Adding **CP 490** extends the process, which needs to be taken into consideration while the cabin drying conditions are being set.

Date of minimum durability:

24 months (in the original unopened package)

*The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products - according to the technical data sheet and execute the sample spray prior to target painting.*