

## CP 999

Fade out binder



Shading resin is a single-component product used for painting car bodies. It is intended to balance the color difference between the special coat 1K primer and the old coat surface on the surrounding car elements (or on the same element in the case of touch-up paintings).

After applying the **CP 999** resin coat, the special coat 1K shading primer should be applied through the wet-on-wet technique.

With its unique properties, **CP 999** creates no cloud effect on the edges of the applied coat layer and makes the difference unnoticeable.

Unit	Packaging	Collective (box)
1 L		3 pcs



**100 parts of CP 999,**  
**100 parts of thinner CP 048.**



Applied wet-on-wet. Spray gun\*.  
Nozzle opening with the pneumatic method: **1.3-1.4 mm.**  
Operating pressure – High-pressure: **4 bar\***; HVLV: **2 bar\***.

\* Use high pressure equipment and HVLV. Pressure as recommended by the gun manufacturer.

#### Surface preparation:

Clean the surface with a silicone remover.  
Clean the matte surface with gray or gold abrasive pad, preferably with the addition of matting agent paste.

#### Output:

7-8 m<sup>2</sup>/l (layer 40 μm)

#### Date of minimum durability:

24 months (in the original unopened package)

The recipe of the product complies with the VOC guidelines. The products supplied by our company are subject to a number of factory tests, so they can meet the highest demands. However, be aware of the individual conditions of storage, preparation and applications that can influence on the effect of varnishing. The guarantee to keep the highest quality of the coating is to use the product only with the products of the Manufacturer and in accordance with the recommendations of the Manufacturer. The Manufacturer does not guarantee performance and compatibility of the Products with products other than those of the Manufacturer. In order to recognize the guarantee and all claims, the user shall use the technologies and techniques for given Products - according to the technical data sheet and execute the sample spray prior to target painting.